

KCC 4782 (K-C 17,029)  
PATENT

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Previously Presented) A process for manufacturing a cellulosic paper product, the process comprising:  
    forming an aqueous suspension of papermaking fibers;  
    introducing sodium bicarbonate into said aqueous suspension;  
    depositing said aqueous suspension onto a sheet-forming fabric to form a wet web; and  
    through-drying said wet web by passing heated air through said wet web.
2. (Canceled).
3. (Previously Presented) A process as set forth in claim 1 wherein said aqueous suspension has a pH of from about 7.5 to about 8.5 after said sodium bicarbonate is introduced into said suspension.
4. (Original) A process as set forth in claim 3 wherein said aqueous suspension has a pH of about 8.0 after said sodium bicarbonate is introduced into said suspension.
5. (Previously Presented) A process as set forth in claim 1 wherein said sodium bicarbonate is introduced into said aqueous suspension in an amount from about 10 to about 15% by weight of papermaking fiber present in said aqueous suspension.

KCC 4782 (K-C 17,029)  
PATENT

6. (Original) A process as set forth in claim 5 wherein said sodium bicarbonate is introduced into said aqueous suspension in an amount from about 12 to about 13% by weight of papermaking fiber present in said aqueous suspension.

7. (Previously Presented) A process as set forth in claim 1 wherein the temperature of said heated air is at least about 190°C.

8. (Canceled).

9. (Previously Presented) A process as set forth in claim 7 wherein the temperature of said heated air is from about 190° to about 210°C.

10. (Original) A process as set forth in claim 9 wherein the temperature of said heated air is from about 200° to about 205°C.

11. (Original) A process as set forth in claim 1 wherein said papermaking fibers predominantly comprise secondary cellulosic fibers.

12. (Previously Presented) A process for making a cellulosic paper product, the process comprising:  
forming an aqueous suspension of papermaking fibers;  
introducing sodium bicarbonate into said aqueous suspension;  
depositing said aqueous suspension onto a sheet-forming fabric to form a wet web, said sodium bicarbonate being introduced into said aqueous suspension prior to depositing said aqueous suspension onto said sheet-forming fabric; and

KCC 4782 (K-C 17,029)  
PATENT

through-drying said wet web by passing heated air through said wet web.

13. (Original) A process as set forth in claim 12 wherein said aqueous suspension has a pH of from about 7.5 to about 8.5 after said sodium bicarbonate is introduced into said suspension.

14. (Original) A process as set forth in claim 13 wherein said aqueous suspension has a pH of about 8.0 after said sodium bicarbonate is introduced into said suspension.

15. (Original) A process as set forth in claim 12 wherein said sodium bicarbonate is introduced into said aqueous suspension in an amount from about 10 to about 15% by weight of papermaking fiber present in said aqueous suspension.

16. (Original) A process as set forth in claim 15 wherein said sodium bicarbonate is introduced into said aqueous suspension in an amount from about 12 to about 13% by weight of papermaking fiber present in said aqueous suspension.

17. (Original) A process as set forth in claim 12 wherein the temperature of said heated air is at least about 190°C.

18. (Original) A process as set forth in claim 17 wherein the temperature of said heated air is from about 190° to about 210°C.

KCC 4782 (K-C 17,029)  
PATENT

19. (Original) A process as set forth in claim 18 wherein the temperature of said heated air is from about 200° to about 205°C.

20. (Original) A process as set forth in claim 12 wherein said papermaking fibers predominantly comprise secondary cellulosic fibers.

Claims 21-25 (Canceled).

26. (Previously Presented) A process for manufacturing a cellulosic paper product, the process comprising:  
forming an aqueous suspension of papermaking fibers;  
introducing sodium bicarbonate into said aqueous suspension in an amount from about 10 to about 15% by weight of papermaking fiber present in said aqueous suspension;  
depositing said aqueous suspension onto a sheet-forming fabric to form a wet web; and  
through-drying said wet web by passing heated air through said wet web.

27. (Previously Presented) A process as set forth in claim 26 wherein said aqueous suspension has a pH of from about 7.5 to about 8.5 after said sodium bicarbonate is introduced into said suspension.

28. (Previously Presented) A process as set forth in claim 27 wherein said aqueous suspension has a pH of about 8.0 after said sodium bicarbonate is introduced into said suspension.

KCC 4782 (K-C 17,029)  
PATENT

29. (Previously Presented) A process as set forth in claim 26 wherein said sodium bicarbonate is introduced into said aqueous suspension in an amount from about 12 to about 13% by weight of papermaking fiber present in said aqueous suspension.

30. (Previously Presented) A process as set forth in claim 26 wherein the temperature of said heated air is at least about 190°C.

31. (Previously Presented) A process as set forth in claim 30 wherein the temperature of said heated air is from about 190° to about 210°C.

32. (Previously Presented) A process as set forth in claim 31 wherein the temperature of said heated air is from about 200° to about 205°C.

33. (Previously Presented) A process as set forth in claim 26 wherein said papermaking fibers predominantly comprise secondary cellulosic fibers.

34. (Previously Presented) A process for making a cellulosic paper product, the process comprising:  
forming an aqueous suspension of papermaking fibers;  
introducing sodium bicarbonate into said aqueous suspension in an amount from about 10 to about 15% by weight of papermaking fiber present in said aqueous suspension;  
depositing said aqueous suspension onto a sheet-forming fabric to form a wet web, said sodium bicarbonate being

KCC 4782 (K-C 17,029)  
PATENT

introduced into said aqueous suspension prior to depositing said aqueous suspension onto said sheet-forming fabric; and  
through-drying said wet web by passing heated air through said wet web.

35. (Previously Presented) A process as set forth in claim 34 wherein said aqueous suspension has a pH of from about 7.5 to about 8.5 after said sodium bicarbonate is introduced into said suspension.

36. (Previously Presented) A process as set forth in claim 35 wherein said aqueous suspension has a pH of about 8.0 after said sodium bicarbonate is introduced into said suspension.

37. (Previously Presented) A process as set forth in claim 34 wherein said sodium bicarbonate is introduced into said aqueous suspension in an amount from about 12 to about 13% by weight of papermaking fiber present in said aqueous suspension.

38. (Previously Presented) A process as set forth in claim 34 wherein the temperature of said heated air is at least about 190°C.

39. (Previously Presented) A process as set forth in claim 38 wherein the temperature of said heated air is from about 190° to about 210°C.

40. (Previously Presented) A process as set forth in claim 39 wherein the temperature of said heated air is from about 200° to about 205°C.

KCC 4782 (K-C 17,029)  
PATENT

41. (Previously Presented) A process as set forth in claim 34 wherein said papermaking fibers predominantly comprise secondary cellulosic fibers.